



# Low Fogging Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL



1631 Brummel Ave  
Elk Grove Village, IL 60007

(847) 640-1803  
hstmaterials.com

**Technical Data**

**October, 2008**

**Description** 3M™ Low Fogging Adhesive Transfer Tapes 6035 and 6038 are pressure-sensitive transfer tapes which are specially formulated to be low fogging with good adhesion to many lower surface energy materials. These tapes are ideal for use in automotive interior applications.

Construction	Product	3M™ Low Fogging Adhesive Transfer Tapes	
		6035PC	6038PC
	Adhesive:	5.0 mils (127 microns) #300MP Acrylic Adhesive	8.0 mils (203 microns) #300MP Acrylic Adhesive
	Liner:	4.2 mils (107 microns) 58# Polycoated Kraft Paper	4.2 mils (107 microns) 58# Polycoated Kraft Paper
	Product	3M™ Low Fogging Adhesive Transfer Tapes	
		6035PL	6038PL
	Adhesive:	5.0 mils (127 microns) #300MP Acrylic Adhesive	8.0 mils (203 microns) #300MP Acrylic Adhesive
	Liner:	6.2 mils (157 microns) 83# Polycoated Kraft Paper	6.2 mils (157 microns) 86# Polycoated Kraft Paper

**Typical Physical Properties and Performance Characteristics**

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

Flammability Test: (FMVSS 302/SAE J369)	Pass
Automotive Fogging Test: SAE J1756 @ 100°C	99
Adhesion:	ASTM D-3330 (modified) 90° Peel, 12"/minute (305 mm/minute), 2 mil aluminum foil to various surfaces.

# 3M™ Low Fogging Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

## Typical Physical Properties and Performance Characteristics (continued)

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

### 3M™ Low Fogging Adhesive Transfer Tapes 6035PC & 6035PL

Surface	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	102	112	131	143	166	182
Polycarbonate (High Surface Energy Plastic)	89	97	96	105	67	73
Polypropylene (Low Surface Energy Plastic)	NA	NA	73	80	63	69
ABS	NA	NA	93	102	78	85

### 3M™ Low Fogging Adhesive Transfer Tapes 6038PC & 6038PL

Surface	15 Minute Dwell		72 Hour Dwell		72 Hour Dwell @ 158°F	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	165	181	210	230	247	270
Polycarbonate (High Surface Energy Plastic)	125	137	146	160	106	116
Polypropylene (Low Surface Energy Plastic)	NA	NA	96	105	82	90
ABS	NA	NA	143	157	120	131

## Environmental Performance

Temperature Resistance:	Short term: 250°F (121°C).
Humidity Resistance:	No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C).
U.V. Resistance:	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.
Bond Build-Up:	The bond strength of the adhesive increases as a function of time and temperature.
Shelf Life:	Product retains its performance properties for two years from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity.

# 3M™ Low Fogging Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

## Environmental Performance *(continued)*

Properties defined below are based on sample attachment to a stainless steel faceplate material with a 0.002 inch aluminum foil backing. Values are listed based on a 90° peel at 12 inches/minute (305 mm/minute) after a 24 hour dwell. This data is provided as a guideline for the effects on adhesion at the following conditions and should not be used for specification purposes.

Test Condition	3M™ Low Fogging Adhesive Transfer Tapes			
	6035PC & 6035PL		6038PC & 6038PL	
	Oz./In.	N/100 mm	Oz./In.	N/100 mm
Unleaded Gas - 1 hr. @ R.T.	65	71	127	139
Methyl Ethyl Ketone - 1 hr. @ R.T.	39	43	93	102
Oil (10W30) - 72 hrs. @ 120°F (49°C)	114	124	179	196
Weak Acid (pH 4) - 4 hrs. @ R.T.	89	97	139	152
Weak Base (pH 10) - 4 hrs. @ R.T.	81	89	132	145
Water - 100 hrs. @ R.T.	134	147	139	152
7 days @ 90°F (32°C) and 90 R.H.	140	153	215	235
Sodium Chloride Solution (5%) - 72 hrs. @ R.T.	113	124	203	222
Ultraviolet Light - 30 days exposure	191	209	220	241
Temperature Cycling - 4 hrs. @ 158°F (70°C); 4 hrs. @ -20°F (-29°C); 16 hrs. @ R.T. - repeated three times	134	147	200	219

## Available Sizes

1" - 3" (25.4 mm - 76.2 mm) Width: 60 yds (54.8 m) maximum roll size  
 3" - 5" (76.2 mm - 127 mm) Width: 180 yds (165 m) maximum roll size  
 5" - 60" (127 mm - 1524 mm) Width: 360 yds (329 m) maximum roll size  
 Standard core size = 3" (76.2 mm) diameter  
 Width tolerance = ± 1/32" (0.79 mm)  
 Sizes other than above are negotiable

## Application Techniques

- For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol.  
**Note:** Follow the manufacturer's precautions and directions for use when using solvents.
- Bond strength can also be improved with firm application pressure and moderate heat causing the adhesive to develop intimate contact with the bonding surface.
- Ideal adhesive application temperature range is 70°F to 100°F (21°C to 38°C). This is not recommended for application to surfaces at temperatures below 50°F (10°C) because the adhesive becomes too firm to adhere readily. Once properly applied, low temperature holding is satisfactory.

# 3M™ Low Fogging Adhesive Transfer Tapes

6035PC • 6035PL • 6038PC • 6038PL

---

## General Information

- 3M™ Low Fogging Adhesive Transfer Tapes meet OEM fogging specifications.
- Provides excellent bond to a wide variety of smooth surfaces.
- Excellent shear and peel values to both high and low energy surfaces (PP, ABS, painted metal).
- High initial tack for quick and easy assembly line application.
- High temperature resistance to withstand environmental conditions normally associated with automotive interiors.

---

## Application Ideas

- Attaching a wide variety of vibration and sound damping materials.
- Attaching the wiring harness to the automobile headliner.
- Attaching interior panels.
- Attaching glass to rearview mirror assembly.

---

## Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

---

## Warranty, Limited Remedy, and Disclaimer

Many factors beyond 3M's control and uniquely with user's knowledge and control can affect the use and performance of a 3M product in a particular application. User is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application. Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

---

## Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

**ISO 9001:2000**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.



### Industrial Adhesives and Tapes Division Converter Markets

3M Center, Building 21-1W-10, 900 Bush Avenue  
St. Paul, MN 55144-1000  
800-223-7427 • 651-778-4244 (fax)  
www.3M.com/converter



*Recycled Paper*  
40% pre-consumer  
10% post-consumer

3M is a trademark of 3M Company.  
Printed in U.S.A.  
©3M 2008 70-0709-3852-0 (10/08)