

TYPICAL PROPERTIES OF  
**C42ECH**

POLYMER

EPICHLOROHYDRIN (ECH)

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT	SPECIFICATIONS
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	5 - 9 34.4 - 62	ASTM D1056-07.....2B2 ASTM D1056 Suffix's.....B2, F1, M
DENSITY	ASTM D1056	pcf g/cm <sup>3</sup>	15 .240	
WATER ABSORPTION (MAX)	ASTM D1056	%	5	
TENSILE STRENGTH (Typical)	ASTM D412 (DIE A)	psi kPa	90 620.5	<b>FLAMMABILITY SPECIFICATIONS</b>
ELONGATION (Typical)	ASTM D412 (DIE A)	%	175	FMVSS-302.....PASS
TEAR STRENGTH (Typical)	ASTM D624	lb/in	20	<b>ADDITIONAL INFORMATION</b>
COMPRESSION SET (MAX)	ASTM D1056	%	25	Service Temperature -40 °F to 325 °F
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30	
COLOR	N/A	N/A	BLACK	

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728  
TELEPHONE (304) 525-3116 • FAX (304) 523-4316  
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

