

**TYPICAL PROPERTIES OF  
F-8062**

POLYMER

EPDM

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT	SPECIFICATIONS
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	5 - 9 34.4 - 62	ASTM D1056-68.....RE42 ASTM D1056-07.....2A2 ASTM D1056 Suffix's.....B3, C1, F2, M ASTM D6576-07.....Type II B/C Soft / Med TSM 1501G.....2A2 UL157, UL48, UL50, UL50E, UL508..LISTED Contact customer service for exceptions.
DENSITY	ASTM D1056	pcf g/cm <sup>3</sup>	6 - 10 .096 - .160	
COMPRESSION SET (MAX)	ASTM D1056	%	30	
WATER ABSORPTION (MAX)	ASTM D1056	%	10	
TENSILE STRENGTH (Typical)	ASTM D412 (DIE A)	psi kPa	60 413.6	
ELONGATION (Typical)	ASTM D412 (DIE A)	%	125	
TEAR STRENGTH (Typical)	ASTM D624 (DIE C)	lb/in kN/m	7 1.2	
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30	
RESILIENCE (Typical)	ASTM D2632	%	50	
COLOR	N/A	N/A	BLACK	
				<b>FLAMMABILITY SPECIFICATIONS</b>
				FMVSS-302.....PASS (.188" or Thicker)
				<b>ADDITIONAL INFORMATION</b>
				Service Temperature -70°F to 220°F High Intermittent Temp 275°F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

**P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728  
TELEPHONE (304) 525-3116 • FAX (304) 523-4316  
WWW.RUBBERLITE.COM**

Issue Date: 5/19/14