



TYPICAL PROPERTIES OF

P493SHD

<u>POLYMER</u> <u>EPDM</u>

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	9 - 13 62 - 89.6
DENSITY	ASTM D1056	pcf g/cm³	15 .240
WATER ABSORPTION (MAX)	ASTM D1056	%	5
TENSILE STRENGTH (MIN)	ASTM D412 (DIE A)	psi kPa	110 758.4
ELONGATION (MIN)	ASTM D412 (DIE A)	%	200
COMPRESSION SET (MAX)	ASTM D1056	%	25
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30
COLOR	N/A	N/A	BLACK

SPECIFICATIONS			
ASTM D1056-072A3 ASTM D1056 Suffix'sB2, C1, F2, M			
FLAMMABILITY SPECIFICATIONS			
FMVSS-302PASS			
ADDITIONAL INFORMATION			
Service Temperature -67 °F to 300 °F			

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728 TELEPHONE (304) 525-3116 • FAX (304) 523-4316 WWW.RUBBERLITE.COM

Issue Date: 3/5/12

