

### Paint Protection Film (PPF Coated)

Product Thickness (Total)	8.0 mils	(203.2 microns)
---------------------------	----------	-----------------

Thickness (Top Coat)	0.5 mils	(17.7 microns)
----------------------	----------	----------------

Thickness (Base Film)	6.0 mils	(152.4 microns)
-----------------------	----------	-----------------

Thickness (Adhesive)	1.5 mils	(38.1 microns)
----------------------	----------	----------------

Thickness (Liner)	3.5 mils	(88.9 microns)
-------------------	----------	----------------

Tensile Strength	9000 psi	(62 Mpa)	ASTM D638 - 10
------------------	----------	----------	----------------

Tear Strength	575 pli	(102.7 kg/cm)	ASTM D624 - 00 (2007)
---------------	---------	---------------	-----------------------

Elongation at Break	>400%		ASTM D638 - 10
---------------------	-------	--	----------------

Maximum Temperature	240 °F	(116 °C)	
---------------------	--------	----------	--

Chemical Resistance	Isopropyl Alcohol	No Detrimental Effect
---------------------	-------------------	-----------------------

Chemical Resistance	Hexane / Toluene	No Detrimental Effect
---------------------	------------------	-----------------------

Weathering	QUV 2500h	No Detrimental Effect
------------	-----------	-----------------------

Heat Effect	70C 2500h	No Detrimental Effect
-------------	-----------	-----------------------