Rubberlite Incorporated

HST MATERIALS INC
1631 Brummel Ave
Elk Grove Village, IL 60007
(847) 640-1803
hstmaterials.com

TYPICAL PROPERTIES OF

SCE43B

POLYMER **NEOPRENE/EPDM/SBR**

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	9 - 13 62 - 89.6
DENSITY	ASTM D1056	pcf g/cm³	7 - 11 .112- .176
COMPRESSION SET (MAX)	ASTM D1056	%	30
WATER ABSORPTION (MAX)	ASTM D1056	%	10
TENSILE STRENGTH (Typical)	ASTM D412 (DIE A)	psi kPa	100 690
ELONGATION (Typical)	ASTM D412 (DIE A)	%	125
TEAR STRENGTH (Typical)	ASTM D624 (DIE C)	lb/in kN/m	15 2.6
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±30
RESILIENCE (Typical)	ASTM D2632	%	20
COLOR	N/A	N/A	BLACK

SPECIFICATIONS

ASTM D1056-67……...SCE43
ASTM D1056-78……..……..RE43
ASTM D1056-07……..…..2A3
ASTM D1056 Suffix's……..…A1, C1, F1, M
ASTM D6576-07…....Type II A, B, Medium
MIL-R-6130C ……..…II-A Med
MIL-C-3133C MIL STD 670 B……..SCE11
UL48/ UL50 / UL50E/ UL157 / UL508..Listed

FLAMMABILITY SPECIFICATIONS

UL94 HF-1……..……LISTED[1]
FMVSS-302……..(.098" or Thicker)
[1] Contact customer service for thickness data.

ADDITIONAL INFORMATION

Service Temperature	-40 ℉ to 200 ℉
High Intermittent Temp	250 ℉
Thermal Conductivity	.38 Btu-in/hr-Ft^2-℉

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728
TELEPHONE (304) 525-3116 • FAX (304) 523-4316
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

CERTIFIED MANAGEMENT SYSTEM aqa INTERNATIONAL ISO 9001