

## TYPICAL PROPERTIES OF Ensolite® EFO

POLYMER

EPDM

PHYSICAL PROPERTY	TEST METHOD	UNIT OF MEASURE	RESULT
COMPRESSION DEFLECTION 25%	ASTM D1056	psi kPa	1.0 max 6.895 max
DENSITY	ASTM D1056	pcf g/cm <sup>3</sup>	4 – 8 .064 - .128
COMPRESSION SET (MAX)	ASTM D1056	%	25
TENSILE STRENGTH (MIN)	ASTM D412 (DIE A)	psi kPa	15 103.4
ELONGATION (MIN)	ASTM D412 (DIE A)	%	175
CD CHANGE AFTER OVEN AGING	ASTM D1056	%	±20
COLOR	N/A	N/A	BLACK

SPECIFICATIONS
ASTM D1056-68.....SCO10 ASTM D1056-07.....1A0* *Exception to Elevated Temp Compression Set. ASTM D1056 Suffix's...B2, C1, C2, C3, F2, M Chrysler MS-AY-430.....Type 1 Chrysler MS-AY-528.....Type A Chrysler MS-AY-550.....Grade A Ford WSB-M3G102-B2 GMN1101 .....Ultra Soft GMN1106 .....Type 1AA GMW15473.....Class 1 Type 1 Toyota TSK-6505G.....2A1 / 2A2 Contact customer service for exceptions.
FLAMMABILITY SPECIFICATIONS
FMVSS-302.....PASS FAR 25.853 F Part 1 (a)(1)(ii) .....PASS UL94 HF-1, 5VA, V-0.....LISTED <sup>1</sup> <sup>1</sup> Contact customer service for thickness data.
ADDITIONAL INFORMATION
Service Temperature -70 °F to 250 °F

For updates to this document, please refer to our website or contact customer service.

This information is furnished as a guide for selecting materials. Rubberlite Inc. disclaims liability for results or use of this information. It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

P.O. BOX 2965 HUNTINGTON, WEST VIRGINIA 25728  
TELEPHONE (304) 525-3116 • FAX (304) 523-4316  
WWW.RUBBERLITE.COM

Issue Date: 3/5/12

